

TEST REPORT

DATE: 10-07-2024

Page 1 of 1

TEST NUMBER: 0311813

CLIENT	Yangzhou Tuntex Fiber Technologies Co., LTD.
--------	--

TEST METHOD CONDUCTED	AATCC 175 Stain Resistance Pile Floor Coverings
-----------------------	---

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Nexlon Carpet Tile
CONSTRUCTION	Multi-Level Loop Pile
BACKING	Duraback

GENERAL PRINCIPLE

This method is intended for use on pile floor coverings to determine the resistance to staining by acid food colors. Twenty milliliters (ml) of staining solution (Red Dye 40) is applied to an area of the specimen. After 24 hours the stain is cleaned and a visual rating is assessed by use of the AATCC Red 40 Stain Scale, where a grade of 10 is no staining and 1 is severely stained.

TEST RESULTS

SAMPLE IDENTIFICATION	VISUAL RATING
Nexlon Carpet Tile	10

APPROVED BY:



This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, LLC, shall not be used under any circumstance in advertising to the general public.